Subject to technical alterations and printing errors • First edition 08/1994; Revised 03/2018

Product Data Sheet Separation Membrane TGV 21



Water repellent, air permeable membrane of polypropylene, applicable as diffusionable separation layer; e. g. on inverted green roofs or metal decks.

Technical Data

Separation Membrane TGV 21

Thermally bound, water-repellent membrane of 100 % polypropylene.

Thickness: ca. 0.55 mm
Weight: ca. 80 g/m²
Colour: black

Maximum tensile strength: lengthwise 167 N/50mm

crosswise 120 N/50mm

Onward tearing strength: lengthwise 24 N crosswise 30 N

Max. tensile extension

lengthwise / crosswise: 50 %

Effective opening width: Dw = 0.06 mmAir permeability at 1 mbar: $750 \text{ l/(m}^2 \cdot \text{s})$

Water vapour permeability of air layer thickness according to German

Standard DIN 52 615: s_d< 0.01 m

Dimensions:

Roll width ca. 1.60 m


Roll length ca. 250.00 m Order No. 2180 ca. 50.00 m Order No. 2185

Features

- chemically and biologically neutral
- resistant to all naturally occurring acids and alkali
- compatible with bitumen and polystyrene
- non-rotting
- quick and easy installation
- air and vapour permeable
- water repellent

Application Example

"Inverted green roof"



Plant layer "Rockery Type Plants"

Separation Membrane TGV 21

System Substrate "Rockery Type Plants" Filter Sheet SF Floradrain® FD 25-E

Thermal insulation of extruded polystyrene

Root Barrier WSF 40 Sub structure with root

resistant waterproofing

Specification Suggestion

Thermally bound, water repellent sheet of polypropylene, s_d-value < 0.01 m according to German Standard DIN 52 615, air permeability at 1 mbar: 750 l/(m²•s), maximum tensile force lengthwise 167 N/50mm, maximum tensile extension 50 %, delivery and

installation according to manufacturer's instructions.

Make: ZinCo Separation Membrane

TGV 21

Enquiries: ZinCo GmbH, Phone: +49 7022 6003-0

